

### Addisil\* 8101

#### Heat-Curing Silicone Adhesive for Automotive Electronics

**Product Description** **Addisil 8101** silicone adhesive is a one-component heat curable silicone adhesive sealant which will bond to many substrates without a primer and which will cure rapidly at elevated temperatures. This product has a very long working time at room temperature and will not cure completely until exposed to elevated temperatures.

**Addisil 8101** is a grey thixotropic material

#### Key Performance Properties

- One component product - no mixing required
- Room temperature storage
- Very fast cure at elevated temperature (in a range of 110 °C to 230 °C)
- Primerless adhesion to many types of substrates (e.g. PBT, PA, phenolic resins, copper, nickel, aluminum, stainless steel, brass, ceramic and glass)
- No formation of cure by-products; low linear shrinkage
- Non-corrosive to metals and sensitive substrates
- Excellent dielectric properties
- Outstanding performance over a wide temperature range
- Service temperature -50 °C to 250 °C

#### Typical Product Data

Uncured Properties	Addisil 8101
Colour	grey
Viscosity, Pa·s, 10 s <sup>-1</sup>	160 - 650
Vertical Flow, @ 30 min., mm	< 2
Density, g/cm <sup>3</sup>	1.09
Cured Properties (cured 10 min. at 175°C)	Addisil 8101
Hardness, Shore A	43
Elongation, %	580
Tensile Strength, MPa	9.2
Dielectric Strength, DIN 53481, kV/mm(2mm thickness)	27.4
Dielectric Constant, DIN 53483 (50 Hz) (1mm thickness)	2.94
Dissipation Factor, DIN 53483 (50 Hz), tan δ (1mm thickness)	0.0018
Volume Resistivity, DIN 53481 Ω·m (1mm thickness)	2.1 * 10 <sup>11</sup>

**Specifications** Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV1 and RTV2.

**Instructions for Use**

**Compatibility**

**Addisil 8101** silicone adhesive will cure in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a gummy appearance of Addisil 8101 silicone adhesive at the interface between the adhesive and the substrate to be bonded. It is recommended that a sample patch test be performed with Addisil 8101 silicone adhesive to determine substrate compatibility.

**Surface Preparation**


The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of Addisil 8101 silicone adhesive and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the adhesive.

**Bonding**

**Addisil 8101** silicone adhesives offer outstanding adhesion characteristics to a wide variety of different substrates without the need of a primer. For difficult-to-bond-to substrates, or where more aggressive chemical adhesion is desired, using SS4155 silicone primer, available from Momentive performance materials, may enhance the adhesion. To apply the primer, thoroughly clean the surface and let dry. Then apply a uniform film (0.01-0.02 mm) of SS4155 silicone primer and allow the primer to air-dry for one hour or more.

**Curing**

**Addisil 8101** silicone adhesive requires the use of elevated temperatures in order to achieve full cure.



The actual cure time is affected by such things as cross-sectional thickness of the RTV silicone adhesive, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared).



**Handling and Safety**

Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals use with Momentive performance materials Products should be obtained from your suppliers. When solvents are used, proper safety precautions must be observed.

**CAUTION**

**Addisil 8101** silicone adhesive can generate flammable hydrogen gas upon contact with acidic, basic, or oxidizing materials. Such contact should be avoided.

**Shelf Life and Storage**

The warranted shelf life from the material will be indicated by the "use before date" on the associated documents with a minimum of 4 months when stored in the unopened containers at 27 °C or less.

**Availability**

Addisil 8101 is available 20 kg pails and 310 ml cartridges.



PRINCIPAL LOCATIONS – Regional Information

North America	World Headquarters 187 Danbury Road Wilton, CT 06897, USA	T 800.295.2392	F 607.754.7517
Latin America	Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil	T +55.11.4534.9650	F +55.11.4534.9660
Europe, Middle East, Africa and India	D-51368 Leverkusen Germany	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241.750
Pacific	Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	T +81.3.5544.3100	F +81.3.5544.3101

CUSTOMER SERVICE CENTERS

North America	Charleston, WV 25314, USA E cs-na.silicones@momentive.com		
	<ul style="list-style-type: none"> <li>Specialty Fluids</li> <li>UA, Silanes, Resins, and Specialties</li> <li>RTV Products-Elastomers</li> <li>Sealants and Adhesives &amp; Construction</li> </ul>	T 800.523.5862 T 800.334.4674 T 800.332.3390 T 877.943.7325	F 304.746.1654 F 304.746.1623 F 304.746.1623 F 304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	<ul style="list-style-type: none"> <li>Argentina &amp; Chile</li> <li>Brazil</li> <li>Mexico &amp; Central America</li> <li>Venezuela, Ecuador, Peru, Colombia, &amp; Caribbean</li> </ul>	T +54.11.4862.9544 T +55.11.4534.9650 T +52.55.5899.5135 T +58.212.285.2149	F +54.11.4862.9544 F +55.11.4534.9660 F +52.55.5899.5138 F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T 00.800.4321.1000 T +31.164.293.276	F +31.164.241750
Pacific	E cs-ap.silicones@momentive.com		
	<ul style="list-style-type: none"> <li>Japan</li> <li>China</li> <li>Korea</li> <li>Singapore</li> </ul>	T +81.276.20.6182 T +86.21.5050.4666 (ext. 1523) T +82.2.6201.4600 T +65.6220.7022	

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS.

EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.